

泛用級 ABS,POLYLAC[®] D-190

January 1,2016 VIW

材料特性

特性(Properties)	測試方法(Test Method)	測試條件(Test Condition)	單位(Unit)	D-190
引張強度 Tensile Strength	ASTM D638	1/8 " , 6 mm/min	Kg/cm ²	480
延伸率 Tensile Elongation	ASTM D638	1/8 " , 6 mm/min	%	15
彎曲強度 Flexural Strength	ASTM D790	1/4 " , 2.8 mm/min	Kg/cm ²	790
彎曲彈性率 Flexural Modulus	ASTM D790	1/4 " , 2.8 mm/min	Kg/cm ²	26000
IZOD 衝擊強度 Izod Impact Strength	ASTM D256(Notched)	1/4 " , 23 1/8 " , 23	Kg-cm/cm	16 17
流動係數 Melt Flow Index	ASTM D1238	200 , 5kg	g/10min	2.1
硬度 Hardness	ASTM D785	1/2 "	R Scale	110
比重 Specific Gravity	ASTM D792	23	-	1.05
軟化點 Vicat Softening Temp.	ASTM D1525	1/8 " , 50 /hr		105
熱變形溫度 Heat Distortion Temp.	ASTM D648	退火 (85 ×8hr) annealed		99
		未退火 unannealed		88
燃燒率 Flammability	UL 94	-	-	1.5mm HB

以上數據僅代表一般通用數據，不代表每一產品的規格值

若有任何疑問請洽產品推廣課 0511-83121300