

CHIMEI

鎮江奇美化工有限公司
ZHENJIANG CHI MEI CHEMICAL CO., LTD

江苏省镇江市新区大港韩峰路 18 号
No.18,Han Feng Rd., Dagang, Zhenjiang New Area, Jiangsu China
Tel: 0511-83121300 Fax: 0511-83121033

SSBR KIBIPOL®Characteristics PR-1255

特性 Properties	测试方法 Test Method	测试条件 Test Condition	单位 Unit	溶聚丁苯橡胶 SSBR
				PR-1255
慕尼指数 Mooney	ASTM D1646	-	MU	47-55
挥发份 Volatile matter	ASTM D5668	-	wt%	≦0.75
溶液粘度 Solution Viscosity	ASTM D445	5% Styrene Solution	Cps	170±10
凝胶含量 Gel Content	-	-	ppm	≦199
SM含量 SM Content	CHIMEI Method NMR	-	%	≦2
色相 APHA color	ASTM D1209	-	APHA	≦10
比重 Specific Gravity	ASTM D-792	23℃	g/cm3	0.91
包装重量 Bale Weight	-	-	Kg	35
包装膜 Wrapping film	-	-	Type	PS

JANUARY 16, 2020

Notes: These are typical properties only and are not to be construed as specifications. Users should confirm results by their own tests.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested. This test report cannot be reproduced, except in full, without prior written permission of the Company. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this Test Report is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.